SHAPING THE FUTURE OF ADHESIVES SHAPING THE FUTURE OF ADHESIVES SHAPING THE FUTURE OF ADHESIVES SHAPING THE FUTURE OF ADHESIVES SHAPING THE FUTURE OF ADHESIVES

ADVANCED POLYMERS INTERNATIONAL

Technical Data Sheet

Gel-Tac® Adhesive FDA271ND

Product Description

Gel-Tac FDA271ND adhesive is a waterbased microsphere adhesive foruse in applications that require the properties of low tack and clean removability.

Application

Gel-Tad FDA271ND adhesive is designed for transfer coating onto paper substrates. FDA271ND can be coated onto release liner using conventional coating methods such as roll and extrusion systems.

Physical Property

Total Solids:	41% - 43%
Viscosity:	1400cps - 2000cps
pH:	8.5 - 10.0
Vehicle:	Water
Particle Size:	30 micron average

Handling & Storage

Gel-Tac FDA271ND may separate overtime. This is typical for this type of adhesive. Mix before use: adhesive will readily redisperse with mild agitation. Check pH in open coating pans and adjust to 9.9 with ammonium hydroxide solution, if necessary. If the pH of the adhesive falls below 8.5, coagulation may occur. Air operated diaphragm pumps are recommended to pump the adhesive. Avoid the use of high speed centrifugal pumps. The adhesive will clean up with water and mild soap when wet. Dried material may require clean up with a solvent such as acetone or ethyl acetate. Personnel should wear gloves & splash goggles when handling material. Keep containers closed to maintain proper pH. Protect the material from freezing conditions.

Typical Performance Properties

Adhesive coated onto 1 mil. polyester film.
Adhesive coat weight 12 gsm/dry.
900 Peel (PSTCS-1-1)

30 min. dwell	113.8g/2.54 cm
24 hour dwell	93g/2.54 cm
Loop tack	240.7g/2.54 cm
Polyken tack	162.2g/2.54 cm

Shelf Life

Gel-Tac adhesive should be stored at temperatures between 50oF and 100oF. Keep containers closed to maintain stability of the adhesive. Shelf life is 6 months.

Packaging

Gel-Tac® adhesive is supplied in 1000kg totes or 200kg drums.

Regulatory Status

Gel-Tac FDA271ND adhesive is compliant under FD (21 CFR) 175.105.

SHAPING THE FUTURE OF ADHESIVES

Recommendations of Advanced Polymers International, if any, regarding the use of this product are based upon testing methods believed to be reliable. All component materials are of the highest quality and our manufacturing process is conducted in accordance with the highest of standards. However, we do not recommend that this product be used in any way which violates any law or infringes upon any valid patents. We make no warranties, express or implied, regarding this product or its use, including merchantability and fitness for a particular purpose. The manufacturer is not liable for any consequential, incidental or special damages of any kind.

3584 Walters Road, Syracuse, NY USA 13209
Phone: 315.451.1755 Fax: 315.451.9442 www.geltac.com

SHAPING THE FUTURE OF ADHESIVES SHAPING THE FUTURE OF ADHESIVES SHAPING THE FUTURE OF ADHESIVES